




**Part Number:** BMS-0474120-090

Revision 20190529 - Generated 2019-May-29



<b>A</b>	47.50 ± 0.50 mm	1.870 ± 0.020 in
<b>B</b>	41.00 ± 0.50 mm	1.614 ± 0.020 in
<b>C</b>	20.10 ± 0.50 mm	0.791 ± 0.020 in
<b>R</b>	1.5 ± 0.50 mm	0.059 ± 0.020 in
	$\mu_i$ (reference)	90
<b>Mass</b>	(approximate)	230 grams
<b>Core Loss</b>	$\text{Core Loss (mW/cm}^3\text{)} = \frac{f}{\frac{a}{Bpk^3} + \frac{b}{Bpk^{2.3}} + \frac{c}{Bpk^{1.65}}} + d \cdot Bpk^2 \cdot f^2$	
	where $B_{pk}$ expressed in gauss, $f$ expressed in hertz, and: $a=3.80E+09$ , $b=1.38E+09$ , $c=2.89E+06$ , $d=2.20E-14$	
	$B_{pk}$	1000 G
	frequency	50 kHz
	Core Loss (nominal)	294 mW/cm <sup>3</sup>
Core Loss (maximum)	338 mW/cm <sup>3</sup>	
<b>DC Saturation</b>	$\% \mu_i = \frac{1}{a + b \cdot H^c} + d$	
	where $H$ expressed in oersteds, and: $a=0.01$ , $b=1.95E-05$ , $c=1.58$ , $d=0.00$	
	$H_{DC}$	50 Oe
	Percent Initial Perm(nom.)	51.0%
	Percent Initial Perm(min.)	43.8%
<b>Coating/Pkg</b>	Coating Type:	None
	Voltage Breakdown (min.)	N/A
	Limit	N/A
	Package Quantity	60 Pieces/Box

