








Part Number:

EMMS-0552825-060D184

Revision 2021-Nov-24 - Generated 2021-Nov-24



A	54.9 ± 0.81 mm	2.161 ± 0.032 in
B	27.6 ± 0.41 mm	1.087 ± 0.016 in
C	24.61 ± 0.48 mm	0.969 ± 0.019 in
D	18.5 mm (min.)	0.728 in (min.)
E	37.5 mm (min.)	1.476 in (min.)
F	16.8 ± 0.33 mm	0.661 ± 0.013 in
H	18.25 ± 0.25 mm	0.719 ± 0.010 in
Mass	(approximate)	110 grams/half
Magnetic Dimensions	A _e - Eff. Mag. Cross Section	3.32 cm ²
	L _e - Eff. Mag. Path Length	12.3 cm
	V _e - Eff. Core Volume	40.8 cm ³
	WA - Min. Eff. Window Area	3.77 cm ²
	sa - Surface Area	123 cm ²
Inductance	μ _i (reference)	60
	A _L value (nominal)	200 nH/N ²
	Test Winding	N=100, #16 AWG
	Frequency	10 kHz
	Voltage on Agilent 4284A	1.5 V
Core Loss	A _L tolerance	±8%
	$\text{Core Loss (mW/cm}^3\text{)} = \frac{f}{\frac{a}{B_{pk}^3} + \frac{b}{B_{pk}^{2.3}} + \frac{c}{B_{pk}^{1.65}}} + d \cdot B_{pk}^2 \cdot f^2$	
	where B _{pk} expressed in gauss, f expressed in hertz, and: a=7.89E+09, b=7.11E+08, c=8.98E+06, d=2.85E-14	
	B _{pk}	1000 G
	frequency	50 kHz
DC Saturation	Core Loss (nominal)	323 mW/cm ³
	Core Loss (maximum)	372 mW/cm ³
	$\% \mu_i = \frac{1}{a + b \cdot H^c} + d$	
	where H expressed in oersteds, and: a=0.01, b=4.47E-06, c=1.74, d=0.00	
	H _{DC}	100 Oe
Coating/Pkg	Percent Initial Perm(nom.)	42.2%
	Percent Initial Perm(min.)	34.7%
	Coating Type:	None
	Voltage Breakdown (min.)	N/A
	Limit	N/A
Winding Table	Package Quantity	72 Halves/Box
	Wire Size	AWG 8, 10, 12, 14, 16, 18, 20, 22, 24, 26, 28
	mm	3.150, 2.500, 2.000, 1.600, 1.250, 1.000, 0.800, 0.630, 0.500, 0.400, 0.315
	Full Turns	20, 31, 49, 75, 117, 180, 279, 432, 669, 1,036, 1,603
	Winding Rdc(Ω)	3.6 m, 8.9 m, 22.3 m, 54.3 m, 134.8 m, 329.8 m, 812.9 m, 2.0, 4.9, 12.1, 29.9



Handling and Storage: Cores should be stored in the original unopened packaging between -10°C and +50°C and less than 60% relative humidity. After the original packaging is opened, the cores should be stored between -8°C and +25°C less than 30% relative humidity. Gloves should be used when handling uncoated cores. The cores should also be sheltered from rain, moisture, salt water, salt air, plasters, ashes, sulfur, sulfur dioxide, ammonia sulfates, soils, acids, metals shavings, and solvents.

Operating Temperature: Cores can be used continuously at operating temperatures between -60°C and +200°C.

RoHS 2.0, REACH and ISO (TS16949, ISO 9001, ISO 14001) compliant. Statements available for download at www.micrometalsapc.com.

Micrometals Alloy Powder Cores, A Division of Micrometals, Inc. - 5615 E. La Palma Ave., Anaheim, California 92807 USA

Ph: +1-714-970-9400, Toll Free in USA: +1-800-356-5977, Asia Pacific Sales: +852 3106 3736

www.Micrometals.com