



**Part Number:** **FS-015014-8**

Revision 20190529 - Generated 2019-May-29



(If coated, Max./Min. includes coating)

<b>OD</b>	(nom. - bare core)	3.94 mm	0.155 in
	(max.)	4.14 mm	0.163 in
<b>ID</b>	(nom. - bare core)	2.21 mm	0.087 in
	(min.)	2.01 mm	0.079 in
<b>HT</b>	(nom. - bare core)	2.54 mm	0.100 in
	(max.)	2.74 mm	0.108 in
<b>Mass</b>	(approximate)	0.11 grams	
<b>Magnetic Dimensions</b>	A <sub>e</sub> - Eff. Mag. Cross Section	0.0211 cm <sup>2</sup>	
	L <sub>e</sub> - Eff. Mag. Path Length	0.942 cm	
	V <sub>e</sub> - Eff. Core Volume	0.0197 cm <sup>3</sup>	
	WA - Min. Eff. Window Area	0.0317 cm <sup>2</sup>	
	sa - Surface Area	0.776 cm <sup>2</sup>	
	mlt - mean length per turn	0.862 cm	
<b>Inductance</b>	μ <sub>i</sub> (reference)	14	
	A <sub>L</sub> value (nominal)	4 nH/N <sup>2</sup>	
	Test Winding	N=30, #32 AWG	
	Frequency	10 kHz	
	Voltage on Agilent 4284A	0.003 V	
	AL tolerance	±8%	
<b>Core Loss</b>	$\text{Core Loss (mW/cm}^3\text{)} = \frac{f}{\frac{a}{B_{pk}^3} + \frac{b}{B_{pk}^{2.3}} + \frac{c}{B_{pk}^{1.65}}} + d \cdot B_{pk}^2 \cdot f^2$		
	where B <sub>pk</sub> expressed in gauss, f expressed in hertz, and:		
	a=1.000E+06, b=6.131E+07, c=2.047E+06, d=6.095E-14		
	B <sub>pk</sub>	300 G	
	frequency	100 kHz	
<b>DC Saturation</b>	Core Loss (nominal)	399 mW/cm <sup>3</sup>	
	Core Loss (maximum)	459 mW/cm <sup>3</sup>	
	$\% \mu_i = \frac{1}{a + b \cdot H^c} + d$		
	where H expressed in oersteds, and:		
<b>Coating/Pkg</b>	a=1.000E-02, b=2.600E-07, c=1.557, d=0.000		
	H <sub>DC</sub>	200 Oe	
	Percent Initial Perm(nom.)	90.9%	
	Percent Initial Perm(min.)	88.3%	
<b>Coating/Pkg</b>	Coating Type:	Parylene N	
	Voltage Breakdown (min.)	500 Vrms	
	Limit	0.1 mA, 5 s	
	Package Quantity	27,000 Pcs/Box	

<b>Winding Table</b>	<b>Wire Size</b>	AWG	28	30	32	34	36	38	40	42	44	-	-
		mm	0.315	0.250	0.200	0.160	0.125	0.100	0.080	0.063	0.050	-	-
	<b>Single Layer</b>	Turns	12	16	21	26	33	42	53	67	84	-	-
		Rdc(Ω)	22.0 m	46.7 m	97.4 m	191.8 m	387.1 m	783.6 m	1.6	3.2	6.3	-	-
<b>Full Winding</b>	Turns	13	20	31	49	75	116	180	279	431	-	-	
	Rdc(Ω)	23.8 m	58.3 m	143.8 m	361.4 m	879.8 m	2.2	5.3	13.2	32.3	-	-	

