








Part Number: PQFS-272190059-026
 Revision 20200820 - Generated 2020-Aug-20



A	27.2 ± 0.46 mm	1.071 ± 0.018 in											
B	19 ± 0.46 mm	0.748 ± 0.018 in											
C	5.94 ± 0.20 mm	0.234 ± 0.008 in											
D	3.4 mm (min.)	0.134 in (min.)											
E	12 ± 0.46 mm	0.472 ± 0.018 in											
F	22.05 mm (min.)	0.868 in (min.)											
Mass	(approximate)	7.9 grams/half											
Magnetic Dimensions	A _e - Eff. Mag. Cross Section	0.864 cm ²											
	L _e - Eff. Mag. Path Length	3.33 cm											
	V _e - Eff. Core Volume	2.88 cm ³											
	WA - Min. Eff. Window Area	0.326 cm ²											
	sa - Surface Area	20.4 cm ²											
	mlt - mean length per turn	5.35 cm											
Inductance	μ _i (reference)	26											
	A _L value (nominal)	85 nH/N ²											
	Test Winding	N=10, #26 AWG											
	Frequency	10 kHz											
	Voltage on Agilent 4284A	0.038 V											
A _L tolerance	±12%												
Core Loss	$\text{Core Loss (mW/cm}^3\text{)} = \frac{f}{B_{pk}^3} + \frac{b}{B_{pk}^{2.3}} + \frac{c}{B_{pk}^{1.65}} + d \cdot B_{pk}^2 \cdot f^2$												
	where B _{pk} expressed in gauss, f expressed in hertz, and: a=1.00E+06, b=1.68E+08, c=1.47E+06, d=1.55E-14												
	B _{pk}	300 G											
	frequency	100 kHz											
	Core Loss (nominal)	232 mW/cm ³											
Core Loss (maximum)	267 mW/cm ³												
DC Saturation	$\% \mu_i = \frac{1}{a + b \cdot H^c} + d$												
	where H expressed in oersteds, and: a=0.01, b=2.03E-06, c=1.41, d=0.00												
	H _{bc}	200 Oe											
	Percent Initial Perm(nom.)	73.4%											
Percent Initial Perm(min.)	68.1%												
Coating/Pkg	Coating Type:	None											
	Voltage Breakdown (min.)	N/A											
	Limit	N/A											
	Package Quantity	864 Halves/Box											
Winding Table	Wire Size	AWG	18	20	22	24	26	28	30	32	34	36	38
		mm	1.000	0.800	0.630	0.500	0.400	0.315	0.250	0.200	0.160	0.125	0.100
	Full Winding	Turns	16	24	37	58	90	139	215	332	514	796	1,232
		Rdc(Ω)	17.9 m	42.7 m	104.7 m	261.1 m	644.2 m	1.6	3.9	9.6	23.5	58.0	142.7



Handling and Storage: Cores should be stored in the original unopened packaging between -10°C and +50°C and less than 60% relative humidity. After the original packaging is opened, the cores should be stored between -8°C and +25°C less than 30% relative humidity. Gloves should be used when handling uncoated cores. The cores should also be sheltered from rain, moisture, salt water, salt air, plasters, ashes, sulfur, sulfur dioxide, ammonia sulfates, soils, acids, metals shavings, and solvents.

Operating Temperature: Cores can be used continuously at operating temperatures between -60°C and +200°C.

RoHS 2.0, REACH and ISO (TS16949, ISO 9001, ISO 14001) compliant. Statements available for download at www.micrometalsapc.com.