



TEL (714) 970-9400  
USA (800) 356-5977  
FAX (714) 970-0400

### Data Sheet

Part Number: ST200-267

Description: Composite Iron Powder toroidal Core

Finished Dimensions: Inches (millimeters) – includes coating

Outside Diameter:	2.060 Max.	(52.33)
Inside Diameter:	1.200 Min.	(30.48)
Height:	0.815 Max.	(20.70)

#### Magnetic Dimensions:

Magnetic Path Length:	13.0 cm
Cross Sectional Area:	1.83 cm <sup>2</sup> (Combined)
Volume:	23.7 cm <sup>3</sup>

#### Basic Material Characteristics:

Material Type:	Ferrite, 33% + Micrometals Mix -52, 67%
Initial Permeability:	2300 + 75 (reference)
Temperature Stability:	N/A
Color Code:	Green
Finish:	Per UL Card File #E140098 (S)

Inductance Index: 1275nH/N<sup>2</sup> +35%, -25%

Test Winding:	50 turns, AWG-22, single—evenly spaced layer, tightly wound, 1/2" leads
Test Instrument:	HP4274A
Test Frequency:	10kHz
Test Voltage:	0.40V (Bpk = 10 gauss)
Inductance:	4304μH / 2391μH
Hi-Pot:	500 Vrms at 60 Hz, 0.1mA, 5 seconds.

Note: The ferrite core material is temperature sensitive and the inductance will increase as the temperature increases. Minimize handling of the wound core during test. Maintain part at +25C for testing. A small gap or parting line between the cores is normal and acceptable, not a cause for rejection. The Thermal Aging Properties on Micrometals Mix -52 are unique to Micrometals alone and not our competitors. Micrometals Color codes are protected by US Patent and Trade Mark Law. All other magnetic properties as described in Micrometals Power Conversion Catalog, Issue L, Feb. 2007. Micrometals Iron Powder Cores comply with the EU Directives 2002/95/EC and 2003/11/EC. Any possible unintentional RoHS trace elements are less than 100 ppm.