



TEL (714) 970-9400  
 USA (800) 356-5977  
 FAX (714) 970-0400

Data Sheet  
 Part Number: ST83-267  
 Description: Composite Iron Powder Toroidal Core

Finished Dimensions: Inches (millimeters) – includes coating

Outside Diameter:	0.865 / 0.805	(21.97 / 20.44)
Inside Diameter:	0.530 / 0.490	(13.46 / 12.45)
Height:	0.425 / 0.375	(10.80 / 9.53)

Magnetic Dimensions:

Magnetic Path Length:	5.37 cm
Cross Sectional Area:	0.398 cm <sup>2</sup> (Combined)
Volume:	2.14 cm <sup>3</sup>

Basic Material Characteristics:

Material Type:	Ferrite, 33% + Micrometals Mix -52, 67%
Initial Permeability:	2300 + 75 (reference)
Temperature Stability:	N/A
Color Code:	Green / Green
Finish:	Per UL Card File #E140098 (S)

Inductance Index: 625nH/N<sup>2</sup> +35%, -25%

Test Winding:	50 turns, AWG-24, single—evenly spaced layer, tightly wound, 1/2" leads
Test Instrument:	HP4274A
Test Frequency:	10 kHz
Test Voltage:	0.09V (Bpk = 10 gauss)
Inductance:	2109μH / 1172μH

Note: The ferrite core material is temperature sensitive and the inductance will increase as the temperature increases. Minimize handling of the wound core during test. Maintain part at +25C for testing. A small gap or parting line between the cores is normal and acceptable, not a cause for rejection. The Thermal Aging Properties on Micrometals Mix -52 are unique to Micrometals alone and not our competitors. Micrometals Color codes are protected by US Patent and Trade Mark Law. All other magnetic properties as described in Micrometals Power Conversion Catalog, Issue L, Feb. 2007. Micrometals Iron Powder Cores comply with the EU Directives 2002/95/EC and 2003/11/EC. Any possible unintentional RoHS trace elements are less than 100 ppm.