




Part Number:

T106-30

Revision 20190524 - Generated 2019-May-30



OD	(nom. - bare core)	26.92 mm	1.060 in
	(max. - after coating)	27.43 mm	1.080 in
ID	(nom. - bare core)	14.48 mm	0.570 in
	(min. - after coating)	13.97 mm	0.550 in
Ht	(nom. - bare core)	11.10 mm	0.437 in
	(max. - after coating)	11.73 mm	0.462 in
Mass	(approximate)	26 grams	
Magnetic Dimensions	A _e - Eff. Mag. Cross Section	0.659 cm ²	
	L _e - Eff. Mag. Path Length	6.49 cm	
	V _e - Eff. Core Volume	4.28 cm ³	
	WA - Min. Eff. Window Area	1.53 cm ²	
	sa - Surface Area	28.1 cm ²	
	mlt - mean length per turn	4.39 cm	
Inductance	μ _i (reference)	22	
	A _L value (nominal)	30 nH/N ²	
	Test Winding	N=100, #28 AWG	
	Frequency	10 kHz	
	Voltage on Agilent 4284A	0.29 V	
	A _L tolerance	±10%	
Core Loss	$\text{Core Loss(mW/cm}^3\text{)}= \frac{f}{\frac{a}{Bpk^3} + \frac{b}{Bpk^{2.3}} + \frac{c}{Bpk^{1.65}}} + d \cdot Bpk^2 \cdot f^2$		
	where B_{pk} expressed in gauss, f expressed in hertz, and: $a=3.30E+08$, $b=2.00E+07$, $c=2.00E+06$, $d=1.10E-13$		
	Bpk	140 G	
	frequency	100 kHz	
	Core Loss (nominal)	129 mW/cm ³	
	Core Loss (maximum)	149 mW/cm ³	
DC Saturation	$\% \mu_i = \frac{1}{a + b \cdot H^c} + d$		
	where H expressed in oersteds, and: $a=1.00E-02$, $b=4.10E-06$, $c=1.34$, $d=0.00$		
	H _{DC}	200 Oe	
	Percent Initial Perm(nom.)	66.7%	
	Percent Initial Perm(min.)	61.1%	
Coating/Pkg	Coating Type:	Green/Gray Epoxy Paint	
	Voltage Breakdown (min.)	500 Vrms, 60Hz	
	Limit	3 mA, 5 s	
	Package Quantity	700 Pcs/Box	

Winding Table	Wire Size	AWG	10	12	14	16	18	20	22	24	26	28	30
		mm	2.500	2.000	1.600	1.250	1.000	0.800	0.630	0.500	0.400	0.315	0.250
	Single Layer	Turns	12	15	20	26	32	41	52	65	82	102	128
		Rdc(Ω)	1.7 m	3.4 m	7.3 m	15.0 m	29.4 m	59.9 m	120.8 m	240.2 m	482.0 m	953.5 m	1.9
	Full Winding	Turns	12	19	30	46	71	110	171	264	409	633	980
		Rdc(Ω)	1.7 m	4.3 m	10.9 m	26.6 m	65.2 m	160.7 m	397.4 m	975.7 m	2.4	5.9	14.6

